

# UK National Annex to Eurocode 2: Design of concrete structures —

## Part 1-1: General rules and rules for buildings

ICS 91.010.30; 91.080.40

## Committees responsible for this National Annex

The preparation of this National Annex was entrusted by Committee B/525, Building and civil engineering structures, to B/525/2, Structural use of concrete, upon which the following bodies were represented:

Association of Consulting Engineers  
 British Cement Association  
 British Precast Concrete Federation Ltd.  
 Building Research Establishment  
 Concrete Society  
 Department of Transport (Highways Agency)  
 Institution of Civil Engineers  
 Institution of Structural Engineers  
 Office of the Deputy Prime Minister  
 Scottish Building Standards Agency  
 UK Steel  
 Co-opted members

This National Annex was published under the authority of the Standards Policy and Strategy Committee on 8 December 2005

© BSI 8 December 2005

First edition December 2005

### Summary of pages

This document comprises a front cover, an inside front cover, page i, a blank page, pages 1 to 20, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

### Amendments issued since publication

Amd. No.	Date	Comments

The following BSI references relate to the work on this National Annex:  
 Committee reference B/525/2  
 Draft for comment 05/30134002

# Contents

	Page
Committees responsible	Inside front cover
Introduction	1
NA.1 Scope	1
NA.2 Nationally Determined Parameters	1
NA.3 Decisions on the status of informative annexes	19
NA.4 References to non-contradictory complementary information	19
Bibliography	20
Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004	2
Table NA.2 — Recommendations for normal-weight concrete quality for exposure classes XC, XD and XS and cover to reinforcement for a 50 year intended working life and 20 mm maximum aggregate size	15
Table NA.3 — Recommendations for normal-weight concrete quality for exposure class XC and cover to reinforcement for a 100 year intended working life and 20 mm maximum aggregate size	17
Table NA.4 — Recommended values of $w_{\max}$	18
Table NA.5 — Basic ratios of span/effective depth for reinforced concrete members without axial compression	18
Table NA.6a) — Minimum mandrel diameter to avoid damage to reinforcement for bars and wire	19
Table NA.6b) — Minimum mandrel diameter to avoid damage to reinforcement for welded reinforcement and fabrics bent after welding	19



## National Annex (informative) to BS EN 1992-1-1:2004, Eurocode 2: Design of concrete structures — Part 1-1: General rules and rules for buildings

### Introduction

This National Annex has been prepared by BSI Subcommittee B/525/2, Structural use of concrete. In the UK it is to be used in conjunction with BS EN 1992-1-1:2004.

#### NA.1 Scope

NA.1.1 This National Annex gives:

a) the UK decisions for the Nationally Determined Parameters described in the following subclauses of BS EN 1992-1-1:2004:

— 2.3.3 (3)	— 4.4.1.3 (4)	— 6.4.3 (6)	— 9.2.1.3 (1)	— 11.3.5 (1)P
— 2.4.2.1 (1)	— 5.1.3 (1)P	— 6.4.4 (1)	— 9.2.1.4 (1)	— 11.3.5 (2)P
— 2.4.2.2 (1)	— 5.2 (5)	— 6.4.5 (3)	— 9.2.2 (4)	— 11.3.7 (1)
— 2.4.2.2 (2)	— 5.5 (4)	— 6.4.5 (4)	— 9.2.2 (5)	— 11.6.1 (1)
— 2.4.2.2 (3)	— 5.6.3 (4)	— 6.5.2 (2)	— 9.2.2 (2)	— 11.6.1 (2)
— 2.4.2.3 (1)	— 5.8.3.1 (1)	— 6.5.4 (4)	— 9.2.2 (7)	— 11.6.2 (1)
— 2.4.2.4 (1)	— 5.8.3.3 (1)	— 6.5.4 (6)	— 9.2.2 (8)	— 11.6.4.1 (1)
— 2.4.2.4 (2)	— 5.8.3.3 (2)	— 6.8.4 (1)	— 9.3.1.1 (3)	— 12.3.1 (1)
— 2.4.2.5 (2)	— 5.8.5 (1)	— 6.8.4 (5)	— 9.5.2 (21)	— 12.6.3 (2)
— 3.1.2 (2)P	— 5.8.6 (3)	— 6.8.6 (1)	— 9.5.2 (2)	— A.2.1 (1)
— 3.1.2 (4)	— 5.10.1 (6)	— 6.8.6 (3)	— 9.5.2 (3)	— A.2.1 (2)
— 3.1.6 (1)P	— 5.10.2.1 (1)P	— 6.8.7 (1)	— 9.5.3 (3)	— A.2.2 (1)
— 3.1.6 (2)P	— 5.10.2.1 (2)	— 7.2 (2)	— 9.6.2 (1)	— A.2.2 (2)
— 3.2.2 (3)P	— 5.10.2.2 (4)	— 7.2 (3)	— 9.6.3 (1)	— A.2.3 (1)
— 3.2.7 (2)	— 5.10.2.2 (5)	— 7.2 (5)	— 9.7 (1)	— C.1 (1)
— 3.3.4 (5)	— 5.10.3 (2)	— 7.3.1 (5)	— 9.8.1 (3)	— C.1 (3)
— 3.3.6 (7)	— 5.10.8 (2)	— 7.3.2 (4)	— 9.8.2.1 (1)	— E.1 (2)
— 4.4.1.2 (3)	— 5.10.8 (3)	— 7.3.4 (3)	— 9.8.3 (1)	— J.1 (3)
— 4.4.1.2 (5)	— 5.10.9 (1)P	— 7.4.2 (2)	— 9.8.3 (2)	— J.2.2 (2)
— 4.4.1.2 (6)	— 6.2.2 (1)	— 8.2 (2)	— 9.8.4 (1)	— J.3 (2)
— 4.4.1.2 (7)	— 6.2.2 (6)	— 8.3 (2)	— 9.8.5 (3)	— J.3 (3)
— 4.4.1.2 (8)	— 6.2.3 (2)	— 8.6 (2)	— 9.10.2.2 (2)	
— 4.4.1.2 (13)	— 6.2.3 (3)	— 8.8 (1)	— 9.10.2.3 (3)	
— 4.4.1.3 (1)P	— 6.2.4 (4)	— 9.2.1.1 (1)	— 9.10.2.3 (4)	
— 4.4.1.3 (3)	— 6.2.4 (6)	— 9.2.1.1 (3)	— 9.10.2.4 (2)	

b) the UK decisions on the status of BS EN 1992-1-2:2004 informative annexes; and

c) references to non-contradictory complementary information.

#### NA.2 Nationally Determined Parameters

UK decisions for the Nationally Determined Parameters described in BS EN 1992-1-1:2004 are given in Table NA.1.

Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
2.3.3 (3)	Value of $d_{\text{joint}}$	30 m	Use the recommended value
2.4.2.1 (1)	Partial factor for shrinkage action $\gamma_{\text{SH}}$	1,0	Use the recommended value
2.4.2.2 (1)	Partial factor for prestress $\gamma_{\text{P, fav}}$	1,0	0,9
2.4.2.2 (2)	Partial factor for prestress $\gamma_{\text{P, unfav}}$	1,3	1,1
2.4.2.2 (3)	Partial factor for prestress $\gamma_{\text{P, unfav}}$ for local effects	1,2	Use the recommended value
2.4.2.3 (1)	Partial factor for fatigue loads $\gamma_{\text{F, fat}}$	1,0	Use the recommended value
2.4.2.4 (1)	Partial factors for materials for ultimate limit states $\gamma_{\text{C}}$ and $\gamma_{\text{S}}$	Table 2.1N	Use the recommended values
2.4.2.4 (2)	Partial factors for materials for serviceability limit states $\gamma_{\text{C}}$ and $\gamma_{\text{S}}$	1,0	Use the recommended value
2.4.2.5 (2)	Value of $k_{\text{f}}$	1,1	Use the recommended value
3.1.2 (2)P	Value of $C_{\text{max}}$	C90/105	Use the recommended value. However, the shear strength of concrete classes higher than C50/60 should be determined by tests, unless there is evidence of satisfactory past performance of the particular mix including the type of aggregates used. Alternatively, shear strength of concrete strength classes higher than C50/60 may be limited to that of C50/60.
3.1.2 (4)	Value of $k_{\text{t}}$	0,85	1,0
3.1.6 (1)P	Value of $\alpha_{\text{cc}}$	1,0	0,85 for compression in flexure and axial loading and 1,0 for other phenomena. However, $\alpha_{\text{cc}}$ may be taken conservatively as 0,85 for all phenomena.
3.1.6 (2)P	Value of $\alpha_{\text{ct}}$	1,0	Use the recommended value
3.2.2 (3)P	Upper limit of $f_{\text{yk}}$	600 MPa	Use the recommended value
3.2.7 (2)	Design assumptions for reinforcement: value of $\epsilon_{\text{ud}}$	0,9 $\epsilon_{\text{uk}}$	Use the recommended value
3.3.4 (5)	Value of $k$	1,1	Use the recommended value

Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004 (continued)

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
3.3.6 (7)	Design assumptions for prestressing tendons: value of $\epsilon_{ud}$	$0,9\epsilon_{uk}$ or if more accurate values are not known: $\epsilon_{ud} = 0,02$ $f_{p0,1k}/f_{pk} = 0,9$	Use the recommended values
4.4.1.2 (3)	Value of $c_{min,b}$	Post-tensioned bonded tendons in rectangular ducts: greater of the smaller dimension or half the greater dimension. Post-tensioned bonded tendons circular ducts: diameter. Pre-tensioned tendons: $1,5 \times$ diameter of strand or plain wire, $2,5 \times$ diameter of indented wire.	Use the recommended values
4.4.1.2 (5)	Structural classification and values of minimum cover due to environmental conditions $c_{min,dur}$	Table 4.3N for structural classification Tables 4.4N and 4.5N for values of $c_{min,dur}$	Use BS 8500-1:2002, Tables A.6, A.7, A.10, A.11, A.12, A.13 and A.14 for recommendations for concrete quality for a particular exposure class and cover reinforcement $c$ . Table NA.2 and Table NA.3 may also be used because they present the same information given in BS 8500-1 but in a more compact form.
4.4.1.2 (6)	Value of $\Delta c_{dur,y}$	0 mm	Use the recommended value
4.4.1.2 (7)	Value of $\Delta c_{dur,st}$	0 mm	0 mm unless justified by reference to specialist literature such as the Concrete Society's guidance on the use of stainless steel reinforcement [1].
4.4.1.2 (8)	Value of $\Delta c_{dur,add}$	0 mm	0 mm unless justified by reference to specialist literature
4.4.1.2 (13)	Value of $k_1, k_2, k_3$	$k_1 = 5$ mm $k_2 = 10$ mm $k_3 = 15$ mm	Use the recommended value
4.4.1.3 (1)P	Value of $\Delta c_{dev}$	10 mm	Use the recommended value
4.4.1.3 (3)	Value of $\Delta c_{dev}$ under controlled conditions	Expressions (4.3N) and (4.4N)	Use the recommended values

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
4.4.1.3 (4)	Values of $k_1$ and $k_2$	$k_1 = 40$ mm $k_2 = 75$ mm	$k_1 = 40$ mm $k_2 = 65$ mm
5.1.3 (1)P	Simplified load arrangements	<p>The following load arrangements should be considered:</p> <p>a) alternate spans carrying the design variable and permanent load (<math>\gamma_Q Q_k + \gamma_G G_k + P_m</math>), other spans carrying only the design permanent load <math>\gamma_G G_k + P_m</math>;</p> <p>b) any two adjacent spans carrying the design variable and permanent loads (<math>\gamma_Q Q_k + \gamma_G G_k + P_m</math>); all other spans carrying only the design permanent load, <math>\gamma_G G_k + P_m</math>.</p>	<p>Use any of the following three options.</p> <p>a) Consider the two load arrangements recommended in the Eurocode for alternate and adjacent spans.</p> <p>b) Consider the two following arrangements for all spans and alternate spans:</p> <ol style="list-style-type: none"> <li>1) all spans carrying the design variable and permanent load (<math>\gamma_Q Q_k + \gamma_G G_k + P_m</math>);</li> <li>2) alternate spans carrying the design variable and permanent load (<math>\gamma_Q Q_k + \gamma_G G_k + P_m</math>), other spans carrying only the design permanent load <math>\gamma_G G_k + P_m</math>; the same value of <math>\gamma_G</math> should be used throughout the structure;</li> </ol> <p>c) For slabs, use the all spans loaded arrangement described in b)1) if:</p> <ol style="list-style-type: none"> <li>1) in a one-way spanning slab the area of each bay exceeds <math>30 \text{ m}^2</math>;</li> <li>2) the ratio of the variable load <math>Q_k</math> to the permanent load <math>G_k</math> does not exceed 1,25; and</li> <li>3) the variable load <math>Q_k</math> does not exceed <math>5 \text{ kN/m}^2</math> excluding partitions.</li> </ol> <p>When analysis is carried out using the load arrangement described in b)1), the resulting support moments except those at the supports of cantilevers should be reduced by 20 %, with a consequential increase in the span moments.</p> <p>In this context a bay means a strip across the full width of a structure bounded on the other two sides by lines of support.</p> <p>The load arrangements in a), b) and c) are drafted using BS EN 1990:2002, Expression (6.10). Although not shown here, they can also be drafted using BS EN 1990:2002, Expressions (6.10a) and (6.10b).</p>
5.2 (5)	Value of $\theta_0$	1/200	Use the recommended value



Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004 (continued)

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
5.5 (4)	Moment redistribution formula: values of $k_1, k_2, k_3, k_4, k_5$ and $k_6$	$k_1 = 0,44$ $k_2 = 1,25(0,6 + 0,001\ 4/\epsilon_{cu2})$ $k_3 = 0,54$ $k_4 = 1,25(0,6 + 0,001\ 4/\epsilon_{cu2})$ $k_5 = 0,7$ $k_6 = 0,8$	For steels with $f_{yk} \leq 500$ MPa $k_1 = k_3 = 0,4$ $k_2 = k_4 = 0,6 + 0,001\ 4/\epsilon_{cu2}$ $k_5 = 0,7$ $k_6 = 0,8$ For steels with $f_{yk} > 500$ MPa, more restrictive values than those given for steels with $f_{yk} \leq 500$ MPa may be need to be used. PD 6687 gives further guidance on the redistribution of bending moments.
5.6.3 (4)	Values of $\theta_{pl,d}$	Figure 5.6N	Use the recommended values
5.8.3.1 (1)	Value of $\lambda_{lim}$	$\lambda_{lim} = 20 \cdot A \cdot B \cdot C / \sqrt{n}$	Use the recommended value
5.8.3.3 (1)	Value of $k_1$	0,31	Use the recommended value
5.8.3.3 (2)	Value of $k_2$	0,62	Use the recommended value
5.8.5 (1)	Methods of second order analysis	Choice of the following two simplified methods. a) Method based on nominal stiffness. b) Method based on nominal curvature.	Use either method
5.8.6 (3)	Value of $\gamma_{cE}$	1,2	Use the recommended value
5.10.1 (6)	Methods to avoid brittle failure of prestressed members	Methods A to E	Any of the methods A to E may be used.
5.10.2.1 (1)P	Maximum stressing force: values of $k_1$ and $k_2$	$k_1 = 0,8$ $k_2 = 0,9$	Use the recommended value
5.10.2.1 (2)	Maximum stressing force: value of $k_3$	0,95	Use the recommended value
5.10.2.2 (4)	Minimum strength of concrete at various stages of prestressing: values of $k_4$ and $k_5$	$k_4 = 50$ % $k_5 = 30$ %	Use the recommended value

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
<b>5.10.2.2 (5)</b>	Increase of stress at time of transfer of prestress: value of $k_6$	$k_6 = 0,7$	Use the recommended value
<b>5.10.3 (2)</b>	Prestressing force immediately after tensioning: values of $k_7$ and $k_8$	$k_7 = 0,75$ $k_8 = 0,85$	Use the recommended value
<b>5.10.8 (2)</b>	Value of $\Delta\sigma_{p,ULS}$	100 MPa	100 MPa unless the tendon is outwith $\beta d$ from the tension face, in which case $\Delta\sigma_{p,ULS} = 0, \beta = 0,1$ for $d \geq 1\,000$ mm; $\beta = 0,25$ for $d \leq 500$ mm; the value of $\beta$ may be interpolated for the values of $d$ between 500 mm and 1 000 mm.
<b>5.10.8 (3)</b>	Values of $\gamma_{\Delta P,sup}$ and $\gamma_{\Delta P,inf}$	$\gamma_{\Delta P,sup} = 1,2$ $\gamma_{\Delta P,inf} = 0,8$ Both values taken as 1,0 if linear analysis with uncracked sections is applied	Use the recommended value
<b>5.10.9 (1)P</b>	Values of $r_{sup}$ and $r_{inf}$	For pre-tensioning, unbonded tendons: $r_{sup} = 1,05$ and $r_{inf} = 0,95$ For post-tensioning, bonded tendons: $r_{sup} = 1,10$ and $r_{inf} = 0,90$ When appropriate measures (e.g. direct measurements of pretensioning) are taken: $r_{sup} = 1,0$ and $r_{inf} = 1,0$	$r_{sup} = 1,0$ $r_{inf} = 1,0$
<b>6.2.2 (1)</b>	Values of $C_{Rd,c}$ , $v_{min}$ , and $k_1$ for normal shear	$C_{Rd,c} = 0,18/\gamma_c$ $v_{min} = 0,035k^{3/2}f_{ck}^{1/2}$ $k_1 = 0,15$	Use the recommended values See also <b>3.1.2 (2)P</b> for a requirement for concrete class > C50/60
<b>6.2.2 (6)</b>	Value of $\nu$	$\nu = 0,6[1 - f_{ck}/250]$	Use the recommended value See also <b>3.1.2 (2)P</b> for a requirement for concrete class > C50/60
<b>6.2.3 (2)</b>	Limiting values of $\cot\theta$	$1 \leq \cot\theta \leq 2,5$	$1 \leq \cot\theta \leq 2,5$ , except in elements in which shear co-exists with externally applied tension (i.e. tension caused by restraint is not considered here). In these elements, $\cot\theta$ should be taken as 1,0.

Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004 (continued)

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
6.2.3 (3)	Values of $\nu_1$ and $\alpha_{cw}$	<p><math>\nu_1 = \nu</math> as described by Expression (6.3N) or takes the values given in Expressions (6.10.aN) and (6.10.bN)</p> <p><math>\alpha_{cw}</math> takes the values given in Expressions (6.11.aN), (6.11.bN) and (6.11.cN)</p>	<p><math>\nu_1 = \nu</math></p> <p>However, if the design stress of the shear reinforcement is below 80 % of the characteristic yield stress <math>f_{yk}</math>, <math>\nu_1</math> may be taken as:</p> <p><math>\nu_1 = 0,54(1 - 0,5\cos\alpha)</math> for <math>f_{ck} \leq 60</math> MPa</p> <p><math>\nu_1 = (0,84 - f_{ck}/200)(1 - 0,5\cos\alpha) &gt; 0,5</math> for <math>f_{ck} \geq 60</math> MPa</p> <p><math>\alpha_{cw}</math> is as follows:</p> <p>1 for non-prestressed structures</p> <p><math>(1 + \sigma_{cp}/f_{cd})</math> for <math>0 &lt; \sigma_{cp} \leq 0,25f_{cd}</math></p> <p>1,25 for <math>0,25f_{cd} &lt; \sigma_{cp} \leq 0,5f_{cd}</math></p> <p><math>2,5(1 - \sigma_{cp}/f_{cd})</math> for <math>0,5f_{cd} &lt; \sigma_{cp} &lt; 1,0f_{cd}</math></p> <p>where:</p> <p><math>\sigma_{cp}</math> is the mean compressive stress, measured positive, in the concrete due to the design axial force. This should be obtained by averaging it over the concrete section taking account of the reinforcement. The value of <math>\sigma_{cp}</math> need not be calculated at a distance less than <math>0,5d\cot\theta</math> from the edge of the support.</p> <p>Note that the values of <math>\nu_1</math> and <math>\alpha_{cw}</math> should not be such as to give rise to a value of <math>V_{Rd,max}</math> greater than <math>200(b_w)^2</math> at sections more than <math>d</math> from the edge of a support. For this purpose the value of <math>b_w</math> does not need to be reduced for ducts.</p> <p>In the case of straight tendons, a high level of prestress (<math>\sigma_{cp}/f_{cd} &gt; 0,5</math>) and thin webs, if the tension and the compression chords are able to carry the whole prestressing force and blocks are provided at the extremity of beams to disperse the prestressing force it may be assumed that the prestressing force is distributed between the chords. In these circumstances, the compression field due to shear only should be considered in the web, i.e. <math>\alpha_{cw} = 1</math>.</p> <p>See also 3.1.2 (2)P for a requirement for concrete class <math>&gt; C50/60</math>.</p>

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
6.2.4 (4)	Range of values of $\cot\theta_f$	$1,0 \leq \cot\theta_f \leq 2,0$ for compression flanges $1,0 \leq \cot\theta_f \leq 1,25$ for tension flanges	Use the recommended value
6.2.4 (6)	Value of $k$	0,4	Use the recommended value
6.4.3 (6)	Values of $\beta$	$\beta = 1,5$ for a corner column $\beta = 1,4$ for an edge column $\beta = 1,15$ for an internal column	Use the recommended values
6.4.4 (1)	Values of $C_{Rd,c}$ , $v_{\min}$ and $k_1$ for punching shear	$C_{Rd,c} = 0,18\gamma_c$ $v_{\min} = 0,035k^{3/2}f_{ck}^{-1/2}$ $k_1 = 0,1$	Use the recommended value See also 3.1.2 (2)P for a requirement for concrete class > C50/60
6.4.5 (3)	The value of maximum punching resistance adjacent to column $V_{Rd,max}$	$V_{Rd,max} = 0,5v f_{cd}$	Use the recommended value
6.4.5 (4)	The distance $kd$ of the outer perimeter of punching shear reinforcement from the perimeter $U_{out}$	$k = 1,5$	$k = 1,5$ unless the perimeter at which reinforcement is no longer required is less than $3d$ from the face of the loaded area/column. In this case the reinforcement should be placed in the zone $0,3d$ and $1,5d$ from the face of the column.
6.5.2 (2)	Value of $v'$	$v' = 1 - f_{ctk}/250$	Use the recommended value
6.5.4 (4)	Value of $k_1$ , $k_2$ , $k_3$	$k_1 = 1,0$ $k_2 = 0,85$ $k_3 = 0,75$	Use the recommended value
6.5.4 (6)	Value of $k_4$	$k_4 = 3,0$	Use the recommended value
6.8.4 (1)	Values of $\gamma_{F,fat}$ and parameters for S-N curves	$\gamma_{F,fat} = 1,0$ Values of parameters for S-N curves for reinforcing steels given in Table 6.3N Values of parameters for S-N curves for prestressing steels given in Table 6.4N	Use the recommended values
6.8.4 (5)	Value of $k_2$	5	To be determined by consulting specialist literature
6.8.6 (1)	Values of $k_1$ and $k_2$	$k_1 = 70$ MPa $k_2 = 35$ MPa	Use the recommended values unless other values are agreed with appropriate authorities

Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004 (continued)

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
6.8.6 (3)	Value of $k_3$	0,9	1,0
6.8.7 (1)	Fatigue: values for $N$ and $k_1$	$N = 10^6$ cycles $k_1 = 0,85$	Use the recommended value
7.2 (2)	Value of $k_1$	0,6	Use the recommended value
7.2 (3)	Value of $k_2$	0,45	Use the recommended value
7.2 (5)	Value of $k_3, k_4, k_5$	$k_3 = 0,8$ $k_4 = 1,0$ $k_5 = 0,75$	Use the recommended value
7.3.1 (5)	Limitations of crack width $w_{max}$	Table 7.1N	Use Table NA.4
7.3.2 (4)	Value of $\sigma_{ct,p}$	$f_{ct,eff}$ in accordance with 7.3.2 (2)	Use the recommended value
7.3.4 (3)	Maximum crack spacing in Expression (7.11): values for $k_3$ and $k_4$	$k_3 = 3,4$ $k_4 = 0,425$	Use the recommended value
7.4.2 (2)	Values of basic span/depth ratios	Table 7.4N	Use Table NA.5
8.2 (2)	Values of $k_1$ and $k_2$	$k_1 = 1$ mm $k_2 = 5$ mm	Use the recommended value
8.3 (2)	Minimum mandrel diameter $\phi_{m,min}$	Table 8.1N	Use in Table NA.6a) and Table NA.6b)
8.6 (2)	Anchorage capacity of a welded bar	$F_{b,td} = l_{ct}\phi\sigma_{td} \leq F_{wd}$	Use the recommended value
8.8 (1)	Additional rules for large diameter bars: limiting bar size	$\phi_{large} > 32$ mm	$\phi_{large} > 40$ mm
9.2.1.1 (1)	Beams: minimum reinforcement areas	$A_{s,min} = 0,26(f_{ct,m}/f_{yk})b_t d \geq 0,001 3b_t d$	Use the recommended value
9.2.1.1 (3)	Beams: maximum reinforcement areas	$A_{s,max} = 0,04A_c$	Use the recommended value

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
9.2.1.2 (1)	Beams: minimum ratio of span bending moment to be assumed at supports in monolithic construction	$\beta_1 = 0,15$	$\beta_1 = 0,25$
9.2.1.4 (1)	Anchorage of bottom reinforcement at an end support: area of steel provided over supports with little or no end fixity in design	$\beta_2 = 0,25$	Use the recommended value
9.2.2 (4)	Minimum ratio of shear reinforcement in the form of links	$\beta_3 = 0,5$	Use the recommended value
9.2.2 (5)	Minimum shear reinforcement	$\rho_{w,min} = (0,08\sqrt{f_{ck}})/f_{yk}$	Use the recommended value
9.2.2 (6)	Maximum longitudinal spacing of shear assemblies	$s_{l,max} = 0,75d(1 + cot\alpha)$	Use the recommended value
9.2.2 (7)	Maximum longitudinal spacing of bent-up bars	$s_{b,max} = 0,6d(1 + cot\alpha)$	Use the recommended value
9.2.2 (8)	Maximum transverse spacing of links	$s_{t,max} = 0,75d \leq 600$ mm	Use the recommended value
9.3.1.1 (3)	Value of $s_{max,slabs}$	For principal reinforcement: $3h \leq 400$ mm For secondary reinforcement: $3,5h \leq 450$ mm Except in areas with concentrated loads or maximum moment where: For principal reinforcement: $2h \leq 250$ mm For secondary reinforcement: $3h \leq 400$ mm	Use the recommended values except for post-tensioned slabs where reference may be made to specialist literature such as The Concrete Society's design handbook [2].
9.5.2 (1)	Minimum diameter of longitudinal reinforcement in columns	$\phi_{min} = 8$ mm	$\phi_{min} = 12$ mm
9.5.2 (2)	Minimum area of longitudinal reinforcement in columns	$A_{s,min} = 0,10N_{Ed}/f_{yd}$ or $0,002A_c$ , whichever is greater	Use the recommended value

Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004 (continued)

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
9.5.2 (3)	Maximum area of longitudinal reinforcement in columns	$A_{s,max} = 0,04A_c$ outside laps unless it can be shown that the integrity of the concrete will not be affected and that the full strength is achieved at the ULS. $A_{s,max} = 0,08A_c$ at laps	The recommended values apply. The designer should consider the practical upper limit taking into account the ability to place the concrete around the rebar. This issue is considered further in PD 6687.
9.5.3 (3)	Maximum spacing of transverse reinforcement in columns $s_{cl,tmax}$	$s_{cl,tmax}$ should take the least of the following three values: a) 20 times the minimum diameter of the longitudinal bars; b) the lesser dimension of the column; c) 400 mm.	Use the recommended value
9.6.2 (1)	Minimum and maximum area of vertical reinforcement in walls	$A_{s,vmin} = 0,002A_c$ $A_{s,vmax} = 0,04A_c$ outside lap locations unless it can be shown that the integrity of the concrete is not affected and that the full strength is achieved at the ULS. This limit may be doubled at laps.	Use the recommended value
9.6.3 (1)	Minimum area of horizontal reinforcement in walls	$A_{s,hmin} = 25\%$ or $0,001A_c$ , whichever is greater	Use the recommended values. Where crack control is important early age thermal and shrinkage effects should be considered explicitly.
9.7 (1)	Minimum area of distribution reinforcement in deep beams	$A_{s,dbmin} = 0,1\%$ but not less than $150\text{ mm}^2/\text{m}$ in each face and in each direction	0,2 % in each face
9.8.1 (3)	Value of $\phi_{min}$ for pile caps	8 mm	Use the recommended value
9.8.2.1 (1)	Value of $\phi_{min}$ for columns and wall footings	8 mm	Use the recommended value
9.8.3 (1)	Value of $\phi_{min}$ for tie beams	8 mm	Use the recommended value
9.8.3 (2)	Minimum downward load for tie beams	$q_1 = 10\text{ kN/m}$	To be determined for each individual project

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
9.8.4 (1)	Values of $q_2$ and $\phi_{\min}$	$q_2 = 5 \text{ MPa}$ $\phi_{\min} = 8 \text{ mm}$	Use the recommended values
9.8.5 (3)	Values of $h_1$ and $A_{s,bpmin}$	$h_1 = 600 \text{ mm}$ $A_{s,bpmin}$ from Table 9.6N	Use the recommended values
9.10.2.2 (2)	Force to be resisted by peripheral tie: values of $q_1$ and $q_2$	$q_1 = 10 \text{ kN/m}$ $q_2 = 70 \text{ kN}$	$q_1 = (20 + 4n_0)$ where $n_0$ is the number of storeys $q_2 = 60 \text{ kN}$
9.10.2.3 (3)	Minimum tensile force that an internal tie is capable of resisting	$F_{\text{tie,int}} = 20 \text{ kN/m}$	$F_{\text{tie,int}} = [(q_k + g_k)/7.5](l_r/5)(F_t) \geq F_t \text{ kN/m}$ where ( $q_k + g_k$ ) is the sum of the average permanent and variable floor loads (in $\text{kN/m}^2$ ); $l_r$ is the greater of the distances (in m) between the centres of the columns, frames or walls supporting any two adjacent floor spans in the direction of the tie under consideration; and $F_t = (20 + 4n_0) \leq 60$ . Maximum spacing of internal ties = $1.5l_r$ .
9.10.2.3 (4)	Internal ties on floors without screed: values of $q_3$ and $q_4$	$q_3 = 20 \text{ kN/m}$ $q_4 = 70 \text{ kN}$	$F_{\text{tie}} = (1/7.5)(g_k + q_k)(l_r/5)F_t \geq F_t \text{ kN/m}$ where ( $g_k + q_k$ ) is the sum of the average permanent and variable floor loads (in $\text{kN/m}^2$ ); $l_r$ is the greater of the distances (in m) between the centres of the columns, frames or walls supporting any two adjacent floor spans in the direction of the tie under consideration; and $F_t = (20 + 4n_0) \leq 60$ . Maximum spacing of transverse ties = $1.5l_r$ .



Table NA.1 — UK decisions for Nationally Determined Parameters described in BS EN 1992-1-1:2004 (continued)

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
9.10.2.4 (2)	Force to be resisted by horizontal ties to external columns and/or walls provided at each floor level: values of $F_{tie, fac}$ and $F_{tie, col}$	$F_{tie, fac} = 20$ kN per metre of the façade $F_{tie, col} = 150$ kN	$F_{tie, fac} = F_{tie, col} =$ the greater of $2F_t \leq l_s/2, 5F_t$ and 3% of the total design ultimate vertical load carried by the column or wall at that level. $F_{tie, fac}$ in kN per metre run of wall. $F_{tie, col}$ in kN per column. Tying of external walls is only required if the peripheral tie is not located within the wall. $l_s$ is the floor to ceiling height in m. PD 6687 gives additional requirements related to the UK building regulations.
11.3.5 (1)P	Value of $\alpha_{lec}$ (lightweight aggregate concrete)	0,85	Use the recommended value
11.3.5 (2)P	Value of $\alpha_{lct}$ (lightweight aggregate concrete)	0,85	Use the recommended value
11.3.7 (1)	Value of $k$	$k = 1,1$ for lightweight aggregate concrete with sand as fine aggregate $k = 1,0$ for lightweight aggregate (both fine and coarse aggregate) concrete	Use the recommended value
11.6.1 (1)	Values of $C_{Rd,c}$ , $v_{1,min}$ and $k_1$	$C_{Rd,c} = 0,15\gamma_c$ $v_{1,min} = 0,30k^{3/2}f_{ck}^{1/2}$ $k_1 = 0,15$	$C_{Rd,c} = 0,15\gamma_c$ $v_{1,min} = 0,03k^{3/2}f_{ck}^{1/2}$ $k_1 = 0,15$
11.6.2 (1)	Value of $v_1$	$v_1 = 0,5\eta_1[1 - f_{ck}/250]$	Use the recommended value
11.6.4.1 (1)	Value of $k_2$	0,08	Use the recommended value
12.3.1 (1)	Values of $\alpha_{cc,pl}$ and $\alpha_{ct,pl}$ (plain concrete)	$\alpha_{cc,pl} = 0,8$ $\alpha_{ct,pl} = 0,8$	$\alpha_{cc,pl} = 0,6$ $\alpha_{ct,pl} = 0,6$
12.6.3 (2)	Value of $k$	1,5	Use the recommended value
A.2.1 (1)	Value of $\gamma_{s,red1}$	1,1	Use the recommended value
A.2.1 (2)	Value of $\gamma_{c,red1}$	1,4	Use the recommended value
A.2.2 (1)	Value of $\gamma_{s,red2}$ and $\gamma_{c,red2}$	$\gamma_{s,red2} = 1,05$ $\gamma_{c,red2} = 1,45$	Use the recommended values
A.2.2 (2)	Value of $\gamma_{c,red3}$	1,35	Use the recommended value

Subclause	Nationally Determined Parameter	Eurocode recommendation	UK decision
<b>A.2.3</b> (1)	Value of $\eta$ and $\gamma_{c,red4}$	$\eta = 0,85$ $\gamma_{c,red4} = 1,3$	Use the recommended values
<b>C.1</b> (1)	Values for fatigue stress range, minimum relative rib area and $\beta$	Table C.2N $\beta = 0,6$	Use the recommended values
<b>C.1</b> (3)	Values of $a$ , $f_{yk}$ , $k$ , $\epsilon_{uk}$	For $f_{yk}$ $a = 10$ MPa For $k$ and $\epsilon_{uk}$ $a = 0$ Minimum and maximum values for $f_{yk}$ , $k$ , $\epsilon_{uk}$ in accordance with Table C.3N	Use the recommended values
<b>E.1</b> (2)	Values of indicative strength classes	Table E.1N	Does not apply in the UK — see the guidance in 4.4.1.2 (5)
<b>J.1</b> (2)	Value of $A_{s,surfmin}$	$0,01A_{ct,ext}$	Does not apply in the UK — see PD 6687 for an alternative Annex J
<b>J.2.2</b> (2)	Value of $\tan\theta$	$0,4 \leq \tan\theta \leq 1$	Does not apply in the UK — see PD 6687 for an alternative Annex J
<b>J.3</b> (2)	Value of $k_1$	0,25	Does not apply in the UK — see PD 6687 for an alternative Annex J
<b>J.3</b> (3)	Value of $k_2$	0,5	Does not apply in the UK — see PD 6687 for an alternative Annex J

**Table NA.2 — Recommendations for normal-weight concrete quality for exposure classes XC, XD and XS and cover to reinforcement for a 50 year intended working life and 20 mm maximum aggregate size**

Exposure conditions <sup>a</sup>		Cement/combination types <sup>b</sup>	Nominal cover ( $c_{min} + \Delta c_{dev}$ ) <sup>c</sup> to reinforcement (including prestressing steel) in mm and associated recommended designed concrete and equivalent designated concrete <sup>d</sup>										
			15 + $\Delta c_{dev}$	20 + $\Delta c_{dev}$	25 + $\Delta c_{dev}$	30 + $\Delta c_{dev}$	35 + $\Delta c_{dev}$	40 + $\Delta c_{dev}$	45 + $\Delta c_{dev}$	50 + $\Delta c_{dev}$			
Carbonation induced corrosion	XC1	All	C20/25, 0,7, 240 or RC25	↔	↔	↔	↔	↔	↔	↔	↔	↔	↔
	XC2	All	—	—	C25/30, 0,65, 260 or RC30	↔	↔	↔	↔	↔	↔	↔	↔
	XC3	All except IVB	—	C40/50, 0,45, 340 or RC50	C32/40, 0,60, 280 or RC35	C28/35, 0,60, 280 or RC35	C25/30, 0,65, 260 or RC30	↔	↔	↔	↔	↔	↔
	XC4	Cyclic wet and dry	—	—	—	—	—	—	—	—	—	—	—
Chloride induced corrosion excluding chlorides from seawater	XD1	All	—	—	C40/50, 0,45, 360	C32/40, 0,55, 320	C28/35, 0,60, 300	↔	↔	↔	↔	↔	↔
	XD2	Wet, rarely dry	—	—	—	C40/50, 0,40, 380	C32/40, 0,50, 340	C28/35, 0,55, 320	↔	↔	↔	↔	↔
	XD3	Cyclic wet and dry	—	—	—	C32/40, 0,40, 380	C25/30, 0,50, 340	C20/25, 0,55, 320	↔	↔	↔	↔	↔
		I, IIA, IIB-S, SRPC	—	—	—	—	—	—	—	—	—	—	—
		IIB-V, IIIA	—	—	—	—	—	—	—	—	—	—	—
		IIIB, IVB	—	—	—	—	—	—	—	—	—	—	—
		I, IIA, IIB-S, SRPC	—	—	—	—	—	—	—	—	—	—	—
		IIB-V, IIIA	—	—	—	—	—	—	—	—	—	—	—
		IIIB, IVB	—	—	—	—	—	—	—	—	—	—	—

NOTE 1 ↔ indicates that the concrete given in the cell to the left applies.  
 NOTE 2 Reference should be made to BS 8500-1:2002, Annex A for selecting the quality of concrete subjected to freeze/thaw conditions and concrete in aggressive ground conditions.

<sup>a</sup> Exposure conditions conform to BS EN 206-1:2000.  
<sup>b</sup> Cement/combination types are defined in BS 8500-2:2002, Table 1.  
<sup>c</sup> For values of  $\Delta c_{dev}$ , see BS EN 1992-1-1:2003, 4.4.1.3 (1) and (3).  
<sup>d</sup> The recommended designed concrete is taken from BS 8500-1:2002 and described in this table in terms of strength class, maximum w/c ratio, minimum cement or combination content in kg/m<sup>3</sup>. The equivalent recommended designated concrete is taken from BS 8500-1:2002 and indicated in this table by the designation RC.

Exposure conditions <sup>a</sup>		Cement/ combination types <sup>b</sup>	Nominal cover ( $c_{min} + \Delta c_{dev}$ ) <sup>c</sup> to reinforcement (including prestressing steel) in mm and associated recommended designed concrete and equivalent designated concrete <sup>d</sup>										
			15 + $\Delta c_{dev}$	20 + $\Delta c_{dev}$	25 + $\Delta c_{dev}$	30 + $\Delta c_{dev}$	35 + $\Delta c_{dev}$	40 + $\Delta c_{dev}$	45 + $\Delta c_{dev}$	50 + $\Delta c_{dev}$			
Seawater induced corrosion	XS1 Airborne salts but no direct contact	I, IIA, IIB-S, SRPC	—	—	—	C50/60, 0,35, 380	C40/50, 0,45, 360	C35/45, 0,50, 340	—	—	—	—	—
		IIB-V, IIIA	—	—	—	C45/55, 0,35, 380	C35/45, 0,45, 360	C32/40, 0,50, 340	—	—	—	—	—
		IIIB, IVB	—	—	—	C35/45, 0,40, 380	C28/35, 0,50, 340	C25/30, 0,55, 320	—	—	—	—	—
XS2	Wet, rarely dry	I, IIA, IIB-S, SRPC	—	—	—	C40/50, 0,40, 380	C32/40, 0,50, 340	C28/35, 0,55, 320	—	—	—	—	—
		IIB-V, IIIA	—	—	—	C35/45, 0,40, 380	C28/35, 0,50, 340	C25/30, 0,55, 320	—	—	—	—	—
		IIIB, IVB	—	—	—	C32/40, 0,40, 380	C25/30, 0,50, 340	C20/25, 0,55, 320	—	—	—	—	—
XS3	Tidal, splash and spray zones	I, IIA, IIB-S, SRPC	—	—	—	—	—	—	—	—	—	C45/55, 0,35, 380	C40/50, 0,40, 380
		IIB-V, IIIA	—	—	—	—	—	—	C35/45, 0,40, 380	C32/40, 0,45, 360	C28/35, 0,50, 340	—	—
		IIIB, IVB	—	—	—	—	—	—	C32/40, 0,40, 380	C28/35, 0,45, 360	C25/30, 0,50, 340	—	—

NOTE 1 ⇨ indicates that the concrete given in the cell to the left applies.

NOTE 2 Reference should be made to BS 8500-1:2002, Annex A for selecting the quality of concrete subjected to freeze/thaw conditions and concrete in aggressive ground conditions.

<sup>a</sup> Exposure conditions conform to BS EN 206-1:2000.

<sup>b</sup> Cement/combination types are defined in BS 8500-2:2002, Table 1.

<sup>c</sup> For values of  $\Delta c_{dev}$ , see BS EN 1992-1-1:2003, 4.4.1.3 (1) and (3).

<sup>d</sup> The recommended designed concrete is taken from BS 8500-1:2002 and described in this table in terms of strength class, maximum w/c ratio, minimum cement or combination content in kg/m<sup>3</sup>. The equivalent recommended designated concrete is taken from BS 8500-1:2002 and indicated in this table by the designation RC.

**Table NA.3 — Recommendations for normal-weight concrete quality for exposure class XC and cover to reinforcement for a 100 year intended working life and 20 mm maximum aggregate size**

Exposure conditions <sup>a</sup>		Cement/ combination types <sup>b</sup>	Nominal cover ( $c_{min} + \Delta c_{dev}$ ) <sup>c</sup> to reinforcement (including prestressing steel) in mm and associated recommended designed concrete and equivalent designated concrete <sup>d</sup>											
			15 + $\Delta c_{dev}$	20 + $\Delta c_{dev}$	25 + $\Delta c_{dev}$	30 + $\Delta c_{dev}$	35 + $\Delta c_{dev}$	40 + $\Delta c_{dev}$	45 + $\Delta c_{dev}$	50 + $\Delta c_{dev}$				
Carbonation induced corrosion	XC1	Dry or permanently wet	All	C20/25, 0,7, 2/40 or RC25	↔	↔	↔	↔	↔	↔	↔	↔	↔	↔
	XC2	Wet, rarely dry	All	—	—	C25/30, 0,65, 2/60 or RC30	↔	↔	↔	↔	↔	↔	↔	↔
	XC3	Moderate humidity	All except IVB	—	—	—	C40/50, 0,45, 3/40 or RC50	C35/45, 0,50, 3/20 or RC45	C32/40, 0,55, 3/30 or RC40	C28/35, 0,60, 2/80 or RC35	↔	↔	↔	↔
	XC4	Cyclic wet and dry												

NOTE 1 ↔ indicates that the concrete given in the cell to the left applies.

NOTE 2 Reference should be made to BS 8500-1:2002 for selection of concrete with a one hundred year intended working life and in XD and XS exposure classes.

<sup>a</sup> Exposure conditions conform to BS EN 206-1:2000.

<sup>b</sup> Cement/combination types are defined in BS 8500-2:2002, Table 1.

<sup>c</sup> For values of  $\Delta c_{dev}$ , see BS EN 1992-1-1:2003, 4.4.1.3 (1) and (3).

<sup>d</sup> The recommended designed concrete is taken from BS 8500-1:2002 and described in this table in terms of strength class, maximum w/c ratio, minimum cement or combination content in kg/m<sup>3</sup>. The equivalent recommended designated concrete is taken from BS 8500-1:2002 and indicated in this table by the designation RC.

**Table NA.4 — Recommended values of  $w_{max}$**

Exposure	Reinforced members and prestressed members without bonded tendons (quasi-permanent load combination) mm	Prestressed members with bonded tendons (frequent load combination) mm
X0, XC1	0,3 <sup>a</sup>	0,2
XC2, XC3, XC4	0,3	0,2 <sup>b</sup>
XD1, XD2, XD3, XS1, XS2, XS3		0,2 and decompression <sup>c</sup>
<sup>a</sup> For X0, XC1 exposure classes, crack width has no influence on durability and this limit is set to produce acceptable appearance. In the absence of specific requirements for appearance this limit may be relaxed. <sup>b</sup> For these exposure classes, in addition, decompression should be checked under the quasi-permanent combination of loads. <sup>c</sup> $w_{max} = 0,2$ mm applies to parts of the member that do not have to be checked for decompression.		

In the absence of specific requirements (e.g. water-tightness), it may be assumed that limiting the calculated crack widths to the values of  $w_{max}$  given in Table NA.4, under the quasi-permanent combination of loads, will generally be satisfactory for reinforced concrete members in buildings with respect to appearance and durability.

The durability of prestressed members may be more critically affected by cracking. In the absence of more detailed requirements, it may be assumed that limiting the calculated crack widths to the values of  $w_{max}$  given in BS EN 1992-1-1:2004, Table 7.1N, under the frequent combination of loads, will generally be satisfactory for prestressed concrete members. The decompression limit requires that all parts of the bonded tendons or duct lie at least 25 mm within concrete in compression.

**Table NA.5 — Basic ratios of span/effective depth for reinforced concrete members without axial compression**

Structural system	$K$	Concrete highly stressed $\rho = 1,5 \%$	Concrete lightly stressed $\rho = 0,5 \%$
Simply supported beam, one- or two-way spanning simply supported slab	1,0	14	20
End span of continuous beam or one-way continuous slab or two-way spanning slab continuous over one long side	1,3	18	26
Interior span of beam or one-way or two-way spanning slab	1,5	20	30
Slab supported on columns without beams (flat slab) (based on longer span)	1,2	17	24
Cantilever	0,4	6	8

NOTE 1 The values given have been chosen to be generally conservative and calculation may frequently show that thinner members are possible.

NOTE 2 For two-way spanning slabs, the check should be carried out on the basis of the shorter span. For flat slabs the longer span should be taken.

NOTE 3 The limits given for flat slabs correspond to a less severe limitation than a mid-span deflection of span/250 relative to the columns. Experience has shown this to be satisfactory.

NOTE 4 The values of  $k$  in the table may not be appropriate when the form-work is struck at an early age or when the construction loads exceed the design load. In these cases, the deflections may need to be calculated using advice in specialist literature, e.g. the Concrete Society's report on deflections in concrete slabs and beams [3] and an article for the Magazine of Concrete Research entitled *Are existing span to depth rules conservative for flat slabs?* [4].

NOTE 5 The ratio of area of reinforcement provided to that required should be limited to 1,5 when the span/depth ratio is adjusted. This limit also applies to any adjustments to span/depth ratio obtained from Expressions (7.16a) or (7.16b) from which this table has been derived for concrete class C30/37.

**Table NA.6a) — Minimum mandrel diameter to avoid damage to reinforcement for bars and wire**

Bar diameter, $\phi$ mm	Minimum mandrel diameter, $\phi_{m,min}$ for bends, hooks and loops (see BS EN 1992-1-1:2004, Figure 8.1) mm
$\leq 16$	$4\phi$
$>16$	$7\phi$

NOTE Scheduling, dimensioning, bending and cutting of reinforcement should generally be in accordance with BS 8666.

**Table NA.6b) — Minimum mandrel diameter to avoid damage to reinforcement for welded reinforcement and fabrics bent after welding**

Location of transverse bar defined as a multiple of the bar diameter bar diameter, $\phi$ mm	Minimum mandrel diameter, $\phi_{m,min}$ mm
Transverse bar inside or outside a bend or centre of a transverse bar $\leq 4\phi$ from a bend	$20\phi$
Centre of transverse bars $>4\phi$ from a bend	$4\phi$ for $\phi \leq 16$
	$7\phi$ for $\phi \leq 20$

NOTE Scheduling, dimensioning, bending and cutting of reinforcement should generally be in accordance with BS 8666.

**NA.3 Decisions on the status of informative annexes**

BS EN 1992-1-1:2004 informative Annexes A, B, D, F, G, H and I may be used in the UK.

BS EN 1992-1-1:2004 informative Annexes E and J are not applicable in the UK. PD 6687 provides an alternative informative Annex J that is acceptable for use in the UK.

**NA.4 References to non-contradictory complementary information****NA.4.1 General references**

The following is a list of references that contain non-contradictory complementary information for use with BS EN 1992-1-1.

- PD 6687:2005, *Background paper to the UK National Annexes to BS EN 1992-1-1 and BS EN 1992-1-2*.
- *Guidance on the use of stainless steel reinforcement*, Technical Report 51, Concrete Society, 1998 [1].
- *Post-tensioned concrete floors — Design handbook*, Technical Report 43, The Concrete Society, 2005 [2].
- *Deflections in concrete slabs and beams*, Technical Report No. 58, Concrete Society, 2005 [3].
- VOLLUM, R.L. and T.R. HOSSAIN, *Are existing span to depth rules conservative for flat slabs?*, Magazine of Concrete Research, vol. 54, issue 6, 2002 [4].
- *Standard method of detailing structural concrete — A manual for best practice*, The Institution of Structural Engineers/Concrete Society, [5].

**NA.4.2 References for conforming to UK Building Regulations 2000**

The Building Regulations 2000 [6] requires that a building shall be constructed so that in the event of an accident the building will not suffer collapse to an extent disproportionate to the cause. Approved Document A to the Building Regulations 2000 [7] cites the details and design approaches in BS 8110 as being one acceptable method of meeting this requirement. BS 8110 will be superseded by BS EN 1992-1-1, however, not all the requirements of BS 8110 feature in BS EN 1992-1-1. Therefore, those requirements of BS 8110 that are not covered by BS EN 1992-1-1 have been incorporated into PD 6687 as non-contradictory complimentary information.

## Bibliography

### Standards publications

BS 8110 (all parts), *Structural use of concrete*.

BS 8550-1:2002, *Concrete — Complementary British Standard to BS EN 206-1 — Part 1: Method of specifying and guidance for the specifier*.

BS 8550-2:2002, *Concrete — Complementary British Standard to BS EN 206-1 — Part 2: Specification for constituent materials and concrete*.

BS 8666, *Scheduling, dimensioning, bending and cutting of steel reinforcement for concrete. Specification*.

BS EN 1990:2002, *Eurocode — Basis of structural design*.

BS EN 206-1:2000, *Concrete — Part 1: Specification, performance, production and conformity*.

PD 6687:2005, *Background paper to the UK National Annexes to BS EN 1992-1-1 and BS EN 1992-1-2*.

### Other publications

[1] CONCRETE SOCIETY. *Guidance on the use of stainless steel reinforcement*, Technical Report 51, Camberley: Concrete Society, 1998.

[2] CONCRETE SOCIETY. *Post-tensioned concrete floors — Design handbook*, Technical Report 43, Camberley: Concrete Society, 2005.

[3] CONCRETE SOCIETY. *Deflections in concrete slabs and beams*, Technical Report No. 58, Camberley: Concrete Society, 2005.

[4] VOLLUM, R.L. and T.R. HOSSAIN. *Are existing span to depth rules conservative for flat slabs?*, Magazine of Concrete Research, vol. 54, issue 6, 2002.

[5] INSTITUTION OF STRUCTURAL ENGINEERS/CONCRETE SOCIETY. *Standard method of detailing structural concrete — A manual for best practice*, London: The Institution of Structural Engineers/Concrete Society, 2006.

[6] UNITED KINGDOM. *The Building Regulations 2000*. London: The Stationery Office.

[7] UNITED KINGDOM. *The Building Regulations 2000 Approved Document A: Structure*. London: The Stationery Office, 2004.





---

---

## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.  
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.  
Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.  
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.  
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.  
Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.  
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.  
Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).